



# Makrolon® 2458

Covestro - Polycarbonates - Polycarbonate

Wednesday, January 29, 2020

## General Information

### Product Description

MVR (300°C/1.2 kg) 19 cm<sup>3</sup>/10 min; medical devices; suitable for ETO and steam sterilization at 121°C; biocompatible according to many ISO 10993-1 test requirements; low viscosity; easy release; injection molding - melt temperature 280 - 320°C; available in transparent and opaque colors

### General

Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Biocompatible • Ethylene Oxide Sterilizable	• Good Mold Release • Low Viscosity	• Steam Sterilizable
Uses	• Medical Devices • Medical/Healthcare Applications		
Agency Ratings	• ISO 10993-Part 1		
RoHS Compliance	• RoHS Compliant		
Appearance	• Clear/Transparent	• Colors Available	
Processing Method	• Injection Molding		

## ASTM & ISO Properties <sup>1</sup>

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density (73°F (23°C))	1.20 g/cm <sup>3</sup>	1.20 g/cm <sup>3</sup>	ISO 1183
Apparent (Bulk) Density <sup>2</sup>	0.66 g/cm <sup>3</sup>	0.66 g/cm <sup>3</sup>	ISO 60
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	20 g/10 min	20 g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	19 cm <sup>3</sup> /10min	19 cm <sup>3</sup> /10min	ISO 1133
Molding Shrinkage			
Across Flow	0.50 to 0.70 %	0.50 to 0.70 %	ISO 2577
Flow	0.50 to 0.70 %	0.50 to 0.70 %	ISO 2577
Across Flow : 536°F (280°C), 0.0787 in (2.00 mm) <sup>3</sup>	0.70 %	0.70 %	ISO 294-4
Flow : 0.0787 in (2.00 mm) <sup>3</sup>	0.65 %	0.65 %	ISO 294-4
Water Absorption			
Saturation, 73°F (23°C)	0.30 %	0.30 %	ISO 62
Equilibrium, 73°F (23°C), 50% RH	0.12 %	0.12 %	
<b>Mechanical</b>			
Tensile Modulus (73°F (23°C))	348000 psi	2400 MPa	ISO 527-2/1
Tensile Stress			
Yield, 73°F (23°C)	9430 psi	65.0 MPa	ISO 527-2/50
Break, 73°F (23°C)	10200 psi	70.0 MPa	
Tensile Strain			
Yield, 73°F (23°C)	6.1 %	6.1 %	ISO 527-2/50
Break, 73°F (23°C)	130 %	130 %	
Nominal Tensile Strain at Break			
73°F (23°C)	> 50 %	> 50 %	ISO 527-2/50

Copyright ©, 2020 PolyOne Distribution Company The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained therefrom. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variation in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the application disclosed. Full-scale testing and end product performance are the responsibility of the user. PolyOne Distribution Company shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond PolyOne Distribution Company's direct control. PolyOne Distribution Company MAKES NO WARRANTIES, EXPRESS OR IMPLIED, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendations, nor as an inducement to practice any patented invention without permission of the patent owner.

# Makrolon® 2458

## Covestro - Polycarbonates - Polycarbonate

Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Creep Modulus			ISO 899-1
1 hr	319000 psi	2200 MPa	
1000 hr	276000 psi	1900 MPa	
Flexural Modulus <sup>4</sup> (73°F (23°C))	341000 psi	2350 MPa	ISO 178
Flexural Stress <sup>4</sup>			ISO 178
73°F (23°C)	14100 psi	97.0 MPa	
3.5% Strain, 73°F (23°C)	10600 psi	73.0 MPa	
Flexural Strain at Flexural Strength <sup>5</sup>			ISO 178
73°F (23°C)	7.1 %	7.1 %	
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Charpy Notched Impact Strength <sup>6</sup>			ISO 179/1eA
-22°F (-30°C), Complete Break	6.7 ft·lb/in <sup>2</sup>	14 kJ/m <sup>2</sup>	
73°F (23°C), Partial Break	31 ft·lb/in <sup>2</sup>	65 kJ/m <sup>2</sup>	
Charpy Unnotched Impact Strength			ISO 179/1eU
-76°F (-60°C)	No Break	No Break	
-22°F (-30°C)	No Break	No Break	
73°F (23°C)	No Break	No Break	
Notched Izod Impact Strength <sup>6</sup>			ISO 180/A
-22°F (-30°C), Complete Break	7.1 ft·lb/in <sup>2</sup>	15 kJ/m <sup>2</sup>	
73°F (23°C), Partial Break	31 ft·lb/in <sup>2</sup>	65 kJ/m <sup>2</sup>	
Multi-Axial Instrumented Impact Energy			ISO 6603-2
-22°F (-30°C)	47.9 ft·lb	65.0 J	
73°F (23°C)	40.6 ft·lb	55.0 J	
Multi-Axial Instrumented Impact Peak Force			ISO 6603-2
-22°F (-30°C)	1350 lbf	6000 N	
73°F (23°C)	1150 lbf	5100 N	
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Ball Indentation Hardness	16700 psi	115 MPa	ISO 2039-1
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Heat Deflection Temperature			
66 psi (0.45 MPa), Unannealed	282 °F	139 °C	ISO 75-2/B
264 psi (1.8 MPa), Unannealed	257 °F	125 °C	ISO 75-2/A
Glass Transition Temperature <sup>7</sup>	295 °F	146 °C	ISO 11357-2
Vicat Softening Temperature			
--	295 °F	146 °C	ISO 306/B120
--	293 °F	145 °C	ISO 306/B50
Ball Pressure Test (280°F (138°C))	Pass	Pass	IEC 60695-10-2
CLTE			ISO 11359-2
Flow : 73 to 131°F (23 to 55°C)	3.6E-5 in/in/°F	6.5E-5 cm/cm/°C	
Transverse : 73 to 131°F (23 to 55°C)	3.6E-5 in/in/°F	6.5E-5 cm/cm/°C	
Thermal Conductivity <sup>8</sup> (73°F (23°C))	1.4 Btu·in/hr/ft <sup>2</sup> /°F	0.20 W/m/K	ISO 8302

Copyright ©, 2020 PolyOne Distribution Company The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained therefrom. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variation in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the application disclosed. Full-scale testing and end product performance are the responsibility of the user. PolyOne Distribution Company shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond PolyOne Distribution Company's direct control. PolyOne Distribution Company MAKES NO WARRANTIES, EXPRESS OR IMPLIED, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendations, nor as an inducement to practice any patented invention without permission of the patent owner.

# Makrolon® 2458

## Covestro - Polycarbonates - Polycarbonate

Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Surface Resistivity	1.0E+16 ohms	1.0E+16 ohms	IEC 60093
Volume Resistivity (73°F (23°C))	1.0E+16 ohms·cm	1.0E+16 ohms·cm	IEC 60093
Electric Strength			IEC 60243-1
73°F (23°C), 0.0394 in (1.00 mm)	860 V/mil	34 kV/mm	
Relative Permittivity			IEC 60250
73°F (23°C), 100 Hz	3.10	3.10	
73°F (23°C), 1 MHz	3.00	3.00	
Dissipation Factor			IEC 60250
73°F (23°C), 100 Hz	5.0E-4	5.0E-4	
73°F (23°C), 1 MHz	9.0E-3	9.0E-3	
Comparative Tracking Index (Solution A)	250 V	250 V	IEC 60112
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Oxygen Index <sup>9</sup>	28 %	28 %	ISO 4589-2
Flash Ignition Temperature	896 °F	480 °C	ASTM D1929
Self Ignition Temperature	1022 °F	550 °C	ASTM D1929
Optical	Typical Value (English)	Typical Value (SI)	Test Method
Refractive Index <sup>10</sup>	1.586	1.586	ISO 489
Transmittance			ISO 13468-2
39.4 mil (1000 µm)	89.0 %	89.0 %	
78.7 mil (2000 µm)	89.0 %	89.0 %	
118 mil (3000 µm)	88.0 %	88.0 %	
157 mil (4000 µm)	87.0 %	87.0 %	
Haze (118 mil (3000 µm))	< 0.800 %	< 0.800 %	ISO 14782
Additional Information	Typical Value (English)	Typical Value (SI)	
ISO Shortname	ISO 7391-PC,MR,(,)- 18-9	ISO 7391-PC,MR,(,)- 18-9	

### Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature - Dry Air Dryer	248 °F	120 °C
Drying Time - Dry Air Dryer	4.0 hr	4.0 hr
Suggested Max Moisture	< 0.020 %	< 0.020 %
Suggested Shot Size	30 to 70 %	30 to 70 %
Rear Temperature	482 to 518 °F	250 to 270 °C
Middle Temperature	518 to 554 °F	270 to 290 °C
Front Temperature	545 to 581 °F	285 to 305 °C
Nozzle Temperature	518 to 581 °F	270 to 305 °C
Processing (Melt) Temp	536 to 608 °F	280 to 320 °C
Mold Temperature	158 to 230 °F	70 to 110 °C
Back Pressure	1450 to 2900 psi	10.0 to 20.0 MPa
Vent Depth	9.8E-4 to 3.0E-3 in	0.025 to 0.075 mm

### Injection Notes

Peripheral Screw Speed: 0.05 - 0.2 m/s  
 Hold Pressure (% of Injection Pressure): 50 - 75%  
 Standard Melt Temperature: 300°C

Copyright ©, 2020 PolyOne Distribution Company The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained therefrom. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variation in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the application disclosed. Full-scale testing and end product performance are the responsibility of the user. PolyOne Distribution Company shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond PolyOne Distribution Company's direct control. PolyOne Distribution Company MAKES NO WARRANTIES, EXPRESS OR IMPLIED, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendations, nor as an inducement to practice any patented invention without permission of the patent owner.

# Makrolon® 2458

## Covestro - Polycarbonates - Polycarbonate

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

---

<sup>2</sup> Pellets

---

<sup>3</sup> 60x60x2mm, 500 bar

---

<sup>4</sup> 0.079 in/min (2.0 mm/min)

---

<sup>5</sup> 2 mm/min

---

<sup>6</sup> 3 mm

---

<sup>7</sup> 10°C/min

---

<sup>8</sup> Across Flow

---

<sup>9</sup> Procedure A

---

<sup>10</sup> Method A