



# STYRON™ 498

Americas Styrenics LLC - High Impact Polystyrene

Wednesday, January 29, 2020

## General Information

### General

Material Status	• Commercial: Active		
Regional Availability	• Latin America	• North America	
Features	• Food Contact Acceptable	• High Gloss	• High Impact Resistance
Uses	• Appliances	• Household Goods	
	• Electrical/Electronic Applications	• Medical/Healthcare Applications	
Agency Ratings	• FDA 21 CFR 177.1640		
UL File Number	• E326906		
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

## ASTM & ISO Properties <sup>1</sup>

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.04	1.04	ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	3.5 g/10 min	3.5 g/10 min	ASTM D1238
Molding Shrinkage - Flow	4.0E-3 to 8.0E-3 in/in	0.40 to 0.80 %	ASTM D955
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus (Injection Molded)	319000 psi	2200 MPa	ASTM D638
Tensile Strength			ASTM D638
Yield, Injection Molded	5220 psi	36.0 MPa	
Break, Injection Molded	4350 psi	30.0 MPa	
Tensile Elongation (Break, Injection Molded)	45 %	45 %	ASTM D638
Flexural Modulus (Injection Molded)	334000 psi	2300 MPa	ASTM D790
Flexural Strength (Injection Molded)	8850 psi	61.0 MPa	ASTM D790
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact			ASTM D256
73°F (23°C), Compression Molded	1.6 ft-lb/in	85 J/m	
73°F (23°C), Injection Molded	2.0 ft-lb/in	110 J/m	
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Rockwell Hardness (R-Scale)	114	114	ASTM D785
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 psi (0.45 MPa), Unannealed	199 °F	93.0 °C	
264 psi (1.8 MPa), Unannealed	181 °F	83.0 °C	
Vicat Softening Temperature	221 °F	105 °C	ASTM D1525
CLTE - Flow	5.0E-5 in/in/°F	9.0E-5 cm/cm/°C	ASTM D696
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating	HB	HB	UL 94

Copyright ©, 2020 PolyOne Distribution Company The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained therefrom. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variation in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the application disclosed. Full-scale testing and end product performance are the responsibility of the user. PolyOne Distribution Company shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond PolyOne Distribution Company's direct control. PolyOne Distribution Company MAKES NO WARRANTIES, EXPRESS OR IMPLIED, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendations, nor as an inducement to practice any patented invention without permission of the patent owner.

# STYRON™ 498

## Americas Styrenics LLC - High Impact Polystyrene

Processing Information		
Injection	Typical Value (English)	Typical Value (SI)
Rear Temperature	424 to 480 °F	218 to 249 °C
Middle Temperature	424 to 480 °F	218 to 249 °C
Front Temperature	390 to 415 °F	199 to 213 °C
Nozzle Temperature	415 to 469 °F	213 to 243 °C
Mold Temperature	60 to 150 °F	16 to 66 °C
Injection Rate	Fast	Fast
Back Pressure	29.0 to 174 psi	0.200 to 1.20 MPa
Cushion	0.250 in	6.35 mm
Extrusion	Typical Value (English)	Typical Value (SI)
Cylinder Zone 1 Temp.	351 to 379 °F	177 to 193 °C
Cylinder Zone 2 Temp.	360 to 399 °F	182 to 204 °C
Cylinder Zone 3 Temp.	370 to 410 °F	188 to 210 °C
Cylinder Zone 4 Temp.	390 to 421 °F	199 to 216 °C
Cylinder Zone 5 Temp.	399 to 430 °F	204 to 221 °C
Adapter Temperature	379 to 450 °F	193 to 232 °C
Melt Temperature	379 to 450 °F	193 to 232 °C
Die Temperature	390 to 450 °F	199 to 232 °C

### Extrusion Notes

Zone 6 Temperature: 204 to 221°C

Melt Pump, Pipes, Screen Changer Temperature: 193 to 232°C

Polish Rolls Temperature: 66 to 104°C

Head Pressure: 10 to 21 MPa

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.