



# HYLON® N1013HL

Ravago Manufacturing Americas - Polyamide 66

Wednesday, January 29, 2020

## General Information

### Product Description

Nylon 66, 13% Glass Filled

### General

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Glass Fiber, 13% Filler by Weight
RoHS Compliance	• RoHS Compliant
UL File Number	• E157012

## ASTM & ISO Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density	1.23	g/cm <sup>3</sup>	ISO 1183
Molding Shrinkage - Flow (0.125 in)	0.60 to 0.90	%	ISO 294-4
Water Absorption (24 hr, 73°F)	1.0	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	17100	psi	ISO 527-2
Tensile Strain (Break)	2.5	%	ISO 527-2
Flexural Modulus	725000	psi	ISO 178
Flexural Stress	26000	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	1.9	ft·lb/in <sup>2</sup>	ISO 179
Notched Izod Impact Strength	1.9	ft·lb/in <sup>2</sup>	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (264 psi, Unannealed)	455	°F	ISO 75-2/A
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.06 in		HB	
0.12 in		HB	

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.